SPECIFICATION DATA SHEET

N-8090 Syntheseal®/Nonasbestos Gasket Material F724900E49M6

Description

N-8090 has a latent cure nitrile butadiene rubber binder and reinforced cellulose fiber. It has excellent oil resistance, good sealing characteristics, and is intended for applications with short duration maximum temperatures up to 180°C (350°F). N-8090 has UL component recognition.

Specification Properties

| <u>Property</u> | <u>Value</u> | Method |
|---------------------------------|---------------------|-------------|
| Density, g/cc(lb/cu.ft) | 1.28 (80) (min.) | ASTM F 1315 |
| Compressibility, % (at 34.5MPa) | 15 - 25 | ASTM F 36 |
| Recovery, % | 35 (min.) | ASTM F 36 |
| Tensile Strength, AMD, MPa(psi) | 13.79 (2000) (min.) | ASTM F 152 |
| Fluid Resistance, IRM903 Oil | | ASTM F 146 |
| Change in Tensile Strength, % | 45 (max.) | |
| Change in Thickness, % | 30 (max.) | |
| Change in Compressibility, % | 50 (max.) | |
| Fluid Resistance, Fuel B | | ASTM F 146 |
| Change in Thickness, % | 20 (max.) | |
| Change in Weight, % | 30 (max.) | |
| Binder Type | Nitrile Butadiene | |

Remarks and Related Documents

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

Interface Performance Materials®, EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Lydall Performance Materials (US), Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Lydall Performance Materials (US), Inc. (LPM). LPM EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL LPM BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Revised 09/24/19 Form SPDS-01 09/17/19 ©2019 Lydall Performance Materials (US), Inc.

For more information, please visit www.InterfaceMaterials.com or contact

TECHNICAL CENTER Lydall Performance Materials (US), Inc. 215 Wohlsen Way Lancaster, PA 17603 USA AE@InterfaceMaterials.com +1.717.207.6000

NORTH AMERICAN SALES OFFICE

Lydall Performance Materials (US), Inc. 22260 Haggerty Road, Suite 200 Northville, MI 48167 USA +1.248.596.2880

ASIA PACIFIC Interface Sealing Solutions Shanghai Co., LTD Unit 14F, No. 728 Yan An Road West, Changning District Shanghai 200050 China +8621.5238.5650

INDIA Lydall Performance Materials India LLP Mandkola Road, Vill. Atta, Sohna, Distt: Mewat, Nuh-122103 (Haryana) +91 8930992166

GERMANY Lydall Performance Materials Altenkirchen GmbH Koblenzer Straße 57610 Altenkirchen Germany +49 26818002-0

EUROPE Lydall Performance Materials Europe Maison Lili Pean 64240 Bonloc France +33 (0) 5.59.29.12.20

